

GEOSYNTHETIC CLAY LINER (GCL)

GEOBEN T434

The product Geoben T434 is a geosynthetic clay liner (GCL) made of natural Wyoming sodium bentonite layer between a woven geotextile and a non-woven geotextile. The product Geoben T434 is assembled by a needlepunch process.

GEOTEXTILES

Property	Method	Metric value	Imperial value	Test frequency
Woven Mass/Area	D5261	105 g/m ² minimum	3.1 oz/vg ² minimum	20 000 m ²
Non-woven Mass/Area	D5261	200 g/m ² minimum	5.9 oz/vg ² minimum	20 000 m ²

BENTONITE

Property	Method	Metric value	Imperial value	Test frequency
Bentonite Swell Index	D5890	24 ml/2g minimum	24 ml/2g minimum	50 000 kg
Bentonite Fluid Loss	D5891	18 ml maximum	18 ml maximum	50 000 kg
Moisture Content	D4643	12% maximum	12% maximum	10 000 m ²
Smectite (Montmorillonite)	XRD	90% minimum	90% minimum	Periodic

BENTONITE GEOCOMPOSITE

Property	Method	Metric value	Imperial value	Test frequency
Bentonite Mass/Area	D5993	3.66 kg/m ² minimum	0.75 lbs/pi ² minimum	4 000 m ²
Tensile Strength	D6768	8.8 kN/m minimum	50 lbs/po minimum	4 000 m ²
Peel Strength	D6496	610 N/m minimum	3.5 lbs/po minimum	4 000 m ²
Permeability	D5887	5 x 10 ⁻⁹ cm/sec max.	5 x 10 ⁻⁹ cm/sec max.	Each batch
Index Flux	D5887	1 x 10 ⁻⁸ m ³ /m ² /sec max.	1 x 10 ⁻⁸ m ³ /m ² /sec max.	Each batch
Internal Shear Strength	D6243	24 kPa typical	500 lbs/pi ² typical	Periodic

DIMENSIONS

Property	Method	Metric value	Imperial value	Test frequency
Standard width		4.4 m	14.4 pi	
Standard length		45.5 m	149.3 pi	
Total area		200,2 m ²	2150pi ²	

The information contained herein is provided without cost or obligation on the part of Sinoco Inc. The individual using this information assumes full responsibility for its use, including that of ensuring that this technical sheet is the latest update by contacting Sinoco Inc. Sinoco Inc. must be informed of any defect or non-compliance of the product before installation. Responsibilities for Sinoco Inc. will be limited to replacement of non-conforming or defective product.

