

NON-WOVEN GEOTEXTILE

Sintex S-140P

PHYSICAL

Property	Method	Metric value
Grab tensile strength	ASTM D-4632	401 N
Grab elongation	ASTM D-4632	50%
Trapezoid tear strength	ASTM D-4533	178 N
CBR puncture resistance	ASTM D-6241	1178 N
UV resistance (500hrs)	ASTM D-4355	70%

HYDRAULIC

Property	Method	Metric value
Permittivity	ASTM D-4491	2.0 sec ⁻¹
Water flow	ASTM D-4491	6095 l/min/m ²
Apparent opening size (AOS)	ASTM D-4751	300 µm

PACKAGING

Property	Method	Metric value
Roll width		3.5/1.75 m
Roll length		150 m
Area per roll		525/263 m ²

The information contained herein is provided without charge or obligation on the part of Sinoco inc. The person having this information in their possession assumes all responsibility for its use, including ensuring that this technical sheet represents the latest update by contacting Sinoco inc. Sinoco inc. must be informed of any defect or non-conformity of the product before installation. The responsibility of Sinoco Inc. will be limited to the replacement of the nonconforming or defective product.

