

WOVEN GEOTEXTILE

Sintex S-315W

PHYSICAL

Property	Method	Metric value
Grab tensile strength	ASTM D-4632	1400 N
Grab elongation	ASTM D-4632	15 %
Trapezoid tear strength	ASTM D-4533	533 N
CBR puncture resistance	ASTM D-6241	4450 N
UV resistance (500hrs)	ASTM D-4355	70%

HYDRAULIC

Property	Method	Metric value
Permittivity	ASTM D-4491	0.05 sec ⁻¹
Water flow	ASTM D-4491	163 l/min/m ²
Apparent opening size (AOS)	ASTM D-4751	425 µm

PACKAGING

Property	Method	Metric value
Roll width		3.8 m
Roll length		110 m
Area per roll		418 m ²

The information contained herein is provided without charge or obligation on the part of Sinoco inc. The person having this information in their possession assumes all responsibility for its use, including ensuring that this technical sheet represents the latest update by contacting Sinoco inc. Sinoco inc. must be informed of any defect or non-conformity of the product before installation. The responsibility of Sinoco Inc. will be limited to the replacement of the nonconforming or defective product.

